



METAL COATING FINISH NOTE:

1. ALL NON-THREADED COMPONENTS, WHICH HAVE NOT BEEN COATED WITH FUSION BONDED EPOXY, SHALL BE COATED USING TWO-COAT SELF-PRIMING EPOXY SYSTEM CARBOLINE 801. AN ACCEPTABLE ALTERNATIVE COATING SYSTEM IS SHERWIN WILLIAMS EPOXY MASTIC B58 SERIES.
2. ALL METAL SURFACES TO BE COATED SHALL RECEIVE SURFACE PREPARATION EQUIVALENT TO POWER TOOL CLEANING (SSPC-SP3) BY POWER WIRE BRUSHING, POWER IMPACT TOOLS, OR POWER SANDERS, OR EQUIVALENT TO BRUSH-OFF BLAST CLEANING (SSPC-SP7) TO REMOVE RUST, MILL SCALE, AND OTHER DETRIMENTAL FOREIGN MATERIALS PRESENT UNTIL AT LEAST TWO-THIRDS OF EACH ELEMENT OF SURFACE AREA IS FREE OF ALL VISIBLE RESIDUE. APPLICATION OF THE EPOXY COATING SYSTEM SHALL FOLLOW IMMEDIATELY AFTER SURFACE PREPARATION. ANY CLEANED AREAS NOT COATED BEFORE CORROSION FORMS SHALL BE RE-CLEANED PRIOR TO THE APPLICATION OF THE EPOXY COATING.



DATE

7/2011

REV

APPENDIX 10L
MISCELLANEOUS WATER DETAILS

ADJUSTABLE PIPE SUPPORT

DRAWING NUMBER

10L-5